

Firm:

Technical Services Report

Subject: EN 388: 2003 TESTING OF GLOVES
REFERENCED "MAXIFLEX / PLUS"

Our ref: SPC0151785/0720/PJD

Date: 18th May 2007

Conditions of Issue:

This report may be forwarded to other parties concerned provided that it is not abbreviated or changed in any way. It must not be published, for example by including it in advertisements, without the prior, written permission of SATRA.

Results given in this report refer only to the samples submitted for analysis and tested by SATRA. Comments are for guidance only and are not part of the reported results. All comments and interpretations are outside the scope of UKAS accreditation and are based on current SATRA knowledge.

A satisfactory test report in no way implies that the product tested is approved by SATRA and no warranty is given as to the performance of the product tested. SATRA shall not be liable for any subsequent loss or damage incurred by the client as a result of information supplied in the report. Uncertainty of measurement for a confidence probability of not less than 95 % has been applied to these results

Tests marked † are not UKAS accredited.

(Page 1 of 2)

INTRODUCTION

Samples of gloves referenced "MAXIFLEX and MAXIFLEX PLUS" were received by SATRA on 16th May 2007 for testing in accordance with EN 388: 2003. Testing was carried out on 17th May 2007.

Requirements

Performance Level	1	2	3	4
6.3 Tear resistance (lowest peak force – newtons)	10	25	50	75

RESULTS

Test/property	Test results	Level achieved
EN 388: 2003 6.3 Tear resistance	Sample MAXIFLEX Max. tearing force (N) 1) 84.9 2) 114.9 3) 82.6 4) 85.7	Level 4
EN 388: 2003 6.3 Tear resistance	Sample MAXIFLEX PLUS Max. tearing force (N) 1) 82.3 2) 104.4 3) 111.9 4) 76.1	Level 4

CONCLUSIONS

The gloves referenced "MAXIFLEX and MAXIFLEX PLUS" received by SATRA on 16th May 2007 have been tested in accordance with EN 388: 2003, and achieved the results given in the table below.

EN 374-1: 2003 Test/Property	Results Achieved
Sample MAXIFLEX - EN 388: 2003 6.3 Tear resistance	Level 4
Sample MAXIFLEX PLUS - EN 388: 2003 6.3 Tear resistance	Level 4

***** END OF REPORT *****